

EYEKANDY™ 2K URETHANE KANDY

Description

EyeKandy™ 2K combines proprietary urethane polymers with premium solvents, U.V. additives, and the true dye based candy pigments to create deep rich colors for that unique color only Kandys can exhibit. May be used with or without clear these colors are versatile and easy to use. Compared to Kandy basecoats these colors look deeper and have less bleed through on graphics applied over them. Metallics and PrismFx make great base colors for these kandys.




Components

- **EKU Series.....EyeKandy™ Urethane Colors**
- **UA Series Polyurethane Activators**
- **UR Series Reducers - Optional**



Suitable Substrates

Apply over 2K urethane primer, or basecoat after proper flash times. The final color and depth of EyeKandy finishes is dependent on the color of the base chosen and the thickness of coats applied. Coarse Metallic bases and bases of PrismFx are well suited for EyeKandy as they give a deep, bright, and often 3D effect.



Mix Ratio

For spray applications mix 4 part EyeKandy 2K color with 1 part UA series urethane activator by volume. Additional reduction may be required for use in an air brush application or to weaken the Kandy blend as desired. Mix gently then strain before use. Spray a test panel before use to adjust gun/technique and to confirm desired look. Pot life of 1-2 hours after



Application

Apply 3-5 medium coats using 75% overlap at a gun distance of 8-10 inches. HVLP or reduced pressure (RP) guns should be equipped with 1.2-1.5 mm tips and generally set for 24-32 psi standard HVLP or 12-18 psi for RP guns. Avoid heavy coats to ensure solvent flashes properly. When painting sides of vehicles walk the entire length of the vehicle spraying before then overlapping 75% (approximately a 2 inch movement) of your previous spray and spraying all the way back down the to the other end of the vehicle side. Do not paint one quarter panel at a time to avoid dark streaks where you overlap. Allow to flash at least 10 minutes between coats. Always prepare a test panel to verify gun settings, effect, and desired color before painting your object. After final coat application allow to flash at least 30 minutes but then apply 2K polyurethane clear for maximum protection. If not cleared immediately allow to cure over night then scuff lightly with 600-800 grit sand paper and apply 2K clear.

Read MSDS of all components before using. Use proper personal protective equipment at all times. For use by professionally trained painters. **KEEP OUT OF REACH OF CHILDREN.** Bayou Innovations, LLC warrants that its products are free from defects at time of shipping. All other warranties and guaranties of any kind whether expressed or implied are disclaimed.